

913048 SUPERFLEX PU PLUS HPR

PU 软管, PU 包裹镀铜钢丝螺旋, 用于抽吸和输送
耐磨损物料。



Polyurethane hose with copper-plated steel

spiral covered with PU for suction and transport of abrasive materials.

商品详情

表面平滑度 SMOOTH SURFACE	*****
柔韧性能 FLEXIBILITY	**
耐磨性能 ABRASION RESISTANCE	*****
适用温度范围 TEMPERATURE RANGE	-30°C + 90°C
抗化学物质 CHEMICAL RESISTANCE	tabella PU
抗压性能 CRUSHING RESISTANCE	****
抗臭氧 OZONE RESISTANCE	*****

符合 CE1935/2004 标准和 UE10/2011 标准规定: 接触食品、干燥食品的介质需要通过在温度 40° C 分别对 A B C 三种模拟液进行 24 小时的测试; 接触油脂食品介质需通过在温度 40° C 时对模拟液体 D2 进行 24 小时测试, 下降系数等于或高于 X/2。

Suitable according to Reg. CE 1935/2004 and Reg. UE 10/2011 for contact with dry foodstuff and with foodstuff that requires a simulating liquid type A B C, and oily and fatty foodstuff with a reduction coefficient equal or superior to X/2, that require a simulating type D2. Migration tests performed at 40°C for 24 hours.

符合: FDA 21 CFR 177.1680, 关于干燥食品的规定。

Complies with FDA 21 CFR 177.1680, for dry foodstuff.

内径 ID Inc	内径 ID mm	壁厚 WALL THICKNESS mm	重量 WEIGHT g/m	弯曲半径 BENDING RADIUS mm	螺旋间距 SPIRAL PITCH mm	螺旋直径 SPIRAL mm	真空度 VACUUM m H2O	每卷长度 COIL LENGTH mt
1 1/4	32	2	750	220	10	1.6×2.0	9	20
1 1/2	38	2	850	250	10	1.6×2.0	9	20
	40	2	900	260	10	1.8×2.2	9	20
2	50	2	1100	300	10	1.8×2.2	9	20
	60	2	1250	320	10	1.8×2.2	9	20
	65	2	1350	350	10	1.8×2.2	9	20
	70	2	1450	400	10	1.8×2.2	9	20
3	76	2	1550	450	10	1.8×2.2	9	20
	80	2	1650	500	10	1.8×2.2	9	20
4	102	2.2	2450	580	11	2.0×2.5	9	20
	110	2.2	2550	630	11	2.0×2.5	9	15
5	127	2.2	2850	700	11	2.0×2.5	9	15
6	152	2.2	3300	900	11	2.0×2.5	9	15
8	203	2.2	5100	1200	11	2.5×3.0	9	15
10	254	2.5	7800	1400	12	3.0×3.5	9	-
12	305	2.5	9000	1600	12	3.0×3.5	9	-